

US009410250B2

(12) United States Patent

Yoshizawa et al.

(43) Date of Latent

(10) **Patent No.:**

US 9,410,250 B2

(45) **Date of Patent:** Aug. 9, 2016

(54) DISCHARGE SURFACE TREATMENT ELECTRODE AND METHOD OF MANUFACTURING THE SAME

(75) Inventors: Hiroki Yoshizawa, Tokyo (JP); Satoshi

Kurita, Tokyo (JP); Mitsutoshi Watanabe, Tokyo (JP); Kyouhei Nomura, Tokyo (JP); Yukihiro Shimoda, Tokyo (JP); Nobuhiko Yunoki, Tokyo (JP); Masanobu

Hasegawa, Tokyo (JP)

(73) Assignee: IHI Corporation, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 1337 days.

(21) Appl. No.: 13/264,002
(22) PCT Filed: Apr. 13, 2010

(86) PCT No.: PCT/JP2010/056593

§ 371 (c)(1),

(2), (4) Date: Oct. 12, 2011

(87) PCT Pub. No.: WO2010/119865

PCT Pub. Date: Oct. 21, 2010

(65) **Prior Publication Data**

US 2012/0037070 A1 Feb. 16, 2012

(30) Foreign Application Priority Data

Apr. 14, 2009 (JP) 2009-097683

(51) **Int. Cl. B22F 3/02** (2 **C23C 26/00** (2

(2006.01) (2006.01)

(Continued)

(52) U.S. Cl.

(Continued)

(58) Field of Classification Search

CPC ... B22F 9/082; B22F 1/0007; B22F 2009/044 See application file for complete search history.

(56) References Cited

U.S. PATENT DOCUMENTS

FOREIGN PATENT DOCUMENTS

CN 1314832 A 9/2001 CN 1798870 A 7/2006 (Continued)

OTHER PUBLICATIONS

International Search Report issued May 25, 2010 in PCT/JP10/056593 filed Apr. 13. 2010.

(Continued)

Primary Examiner — George Wyszomierski Assistant Examiner — Ngoclan T Mai (74) Attorney, Agent, or Firm — Oblon, McClelland, Maier & Neustadt, L.L.P.

(57) ABSTRACT

A discharge surface treatment electrode used in discharge surface treatment for forming a wear-resistant film on a treatment target surface of a workpiece by use of the discharge energy of electric discharges caused between the electrode and the workpiece, the film being made of a material of an electrode or a substance obtained by a reaction of the material of the electrode with the discharge energy. The discharge surface treatment electrode is formed by: compression-molding a mixed powder into a green compact, the mixed powder being formed from a powder of a Stellite alloy with an average particle size of 3 µm or less prepared by use of a jet mill and a powder of a metal with an average particle size of 3 µm or less manufactured through an atomization process or a chemical process; and subjecting the green compact to heat treatment.

6 Claims, 4 Drawing Sheets

